

10/559391

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
27 April 2006 (27.04.2006)

PCT

(10) International Publication Number
WO 2006/043751 A1(51) International Patent Classification:⁷ C08F 2/02,
290/04(74) Agent: CHO, In-jae; NewKorea International Patent &
Law, OFFICE 3rd Fl., Janghyun Bldg., 637-23, Yeoksam-
dong, Gangnam-gu, Seoul 135-909 (KR).(21) International Application Number:
PCT/KR2005/002973(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM,
SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN,
YU, ZA, ZM, ZW.(22) International Filing Date:
8 September 2005 (08.09.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10-2004-0071586
8 September 2004 (08.09.2004) KR(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).(71) Applicant (*for all designated States except US*): LG
CHEM, LTD. [KR/KR]; LG Twin Towers, East Tower 20,
Yeouido-dong, Yeongdeungpo-gu, Seoul 150-721 (KR).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): LEE, Jae-gwan
[KR/KR]; #302, 390-9, Jeonmin-dong, Yuseong-gu,
Daejeon 305-810 (KR). KIM, No-ma [KR/KR]; 101-101,
Woosung Apt., Doryong-dong, Yuseong-gu, Daejeon
305-340 (KR). CHANG, Suk-ky [KR/KR]; 106-701,
Lucky Hana Apt., Sinseong-dong, Yuseong-gu, Daejeon
305-721 (KR).

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR PRODUCING AN (METH)ACRYLATE SYRUP

(57) Abstract: Disclosed is a method for producing (meth)acrylate syrup, the method comprising initiating polymerization using the following components at a temperature of 50-80 °C: a (meth)acrylate ester monomer, a chain transfer agent, a diacyl peroxide initiator, and 0.5-3.0 moles, based on 1 mole of the diacyl peroxide initiator, of a tertiary amine cocatalyst. In the disclosed method, a reaction runaway does not occur even in bulk polymerization, it is easy to control molecular weight and it is possible to form a high-molecular weight (meth)acrylate syrup without stirring failure.

WO 2006/043751 A1

BEST AVAILABLE COPY

PCT/KR2005/002973

RO/KR 08.11.2005

METHOD FOR PRODUCING AN (METH)ACRYLATE SYRUP

Technical Field

5

The present invention relates to a method for producing (meth)acrylate syrup. More particularly, the present invention relates to a method for producing (meth)acrylate syrup, in which reaction runaway does not occur even in bulk polymerization, it is easy to control molecular weight and it is possible to form a high-
10 molecular weight (meth)acrylate syrup.

Background Art

In the prior art, (meth)acrylic resin compositions have been used in various
15 applications, such as adhesive sheets, protective coating films and adhesives, because they have excellent transparency and it is easy to control the adhesion their cured material to various substrates. Although these materials for use in the respective applications became highly functional, the use of solution polymerization, emulsion polymerization or suspension polymerization for their production required much energy
20 for the removal of residues. Also, in the use of this polymerization process, it was difficult to exhibit high function, and the load to environment was high. For these reasons, it is a tendency to produce (meth)acrylate by bulk polymerization or photopolymerization which is carried out in the absence of solvents.

The most difficult point in carrying out this bulk polymerization or
25 photopolymerization is that, because a solvent to disperse exothermic heat is not used,

PCT/KR2005/002973

RO/KR 08.11.2005

the reactor temperature is difficult to control, resulting in a high possibility for reaction runaway.

In carrying out bulk polymerization in a general batch reactor, heat transfer is difficult due to the absence of solvent, and the termination of production of radicals is reduced due to a rapid increase in viscosity resulting from an increase in conversion rate. Thus, a phenomenon, such as the partial formation of gel, occurs, and non-uniform resin is liable to be obtained.

To overcome the problems of difficult heat transfer and viscosity increase, the use of a semi-batch, continuous or plug flow reactor in place of the batch reactor has been reported. Japanese patent laid-open publication Nos. Sho 40-003701, Hei 11-255828 and 2000-159816 disclose high-temperature polymerization with the use of this continuous polymerization method. However, the polymerization in this reactor has a problem in that it has a high economic burden, because not only the reactor itself is expensive but also the cost of utilities is significant. Another problem is that it is unfavorable for the production of large amounts of a few species, although it is suitable for the production of small amounts of many different species.

In an attempt to solve these problems, a method is known that carries out polymerization in the batch reactor under the mildest possible conditions. This is a method where the temperature of a reaction system is maintained at a constant level while forcibly terminating polymerization when the conversion or viscosity of the reaction system reaches a given level. Regarding the method for the termination of polymerization, Japanese patent laid-open publication No. Hei 1-011652 discloses the termination of polymerization by the addition of a polymerization inhibitor, and Japanese patent laid-open publication No. Hei 9-067495 discloses polymerization termination, such as quenching by the addition of monomers. However, this

PCT/KR2005/002973

RO/KR 08.11.2005

polymerization method cannot become a fundamental solution because it has shortcomings in that it causes a great increase in viscosity at the latter half of reaction, shows a difference in physical properties depending on the time point of completion of reaction, and results in polymer syrup with poor storage stability because a polymerization inhibitor remains in the syrup.

In an attempt to solve these problems, there have been many solutions where a batch reactor is used but reaction runaway does not occur and the molecular weight of syrup is easily controlled.

First, there are examples where bulk polymerization was carried out without causing reaction runaway due to the non-use of a polymerization initiator. Japanese patent laid-open publication No. 2001-031709 discloses carrying out the bulk polymerization of a compound with a thiol group without a hydroxyl group or a compound with both a hydroxyl group and a thiol group in the substantial absence of an initiator. Also, Japanese patent laid-open publication No. 2001-302705 discloses carrying out the bulk polymerization of a compound with both a thiol group and a carboxyl group in the substantial absence of an initiator. However, these methods have a problem in that the polymerization needs to be conducted at relatively high temperature, because the reaction is made by the transfer of thermally generated radicals in the absence of the initiator so that the reaction rate is very slow. Another problem is that the polymerization efficiency is low.

Also, there is a case where an initiator with low half-life temperature is used. Japanese patent laid-open publication No. 2000-313704 discloses synthesizing an acrylate syrup with a conversion rate of 10-50%, in which 0.001-5.0 parts by weight of an polymerization initiator with a 10-hr half-life temperature of less than 41 °C is used, the self-heat generation at a reaction temperature of 20-80 °C is used, and the peak

PCT/KR2005/002973

RO/KR 08.11.2005

exothermic temperature of reactants reaches a range of 100-140 °C. In this polymerization method, because the self-heat generation is used, the desired object can be achieved only if a very rapid increase in the concentration of radicals at the initial stage of reaction is made. It is considered that the very rapid increase in the concentration of radicals at the initial stage of reaction shows a rapid increase in conversion rate and the peak exothermic temperature, but after that, the reaction is stabilized and reaction runaway does not occur, because most of the initiator is already consumed. However, this method requires care since it is very difficult to handle and store initiators with low half-life temperature.

10 Meanwhile, when an initiator with relatively high half-life temperature is used alone in exothermic polymerization, it is needed to adjust initial reaction temperature to high temperature (10-hr half-life temperature of initiator + 20 °C) in order to cause a rapid increase in the concentration of radicals at the initial stage of reaction. However, this high initial temperature of reaction has problems in that it leads to an increase in the peak exothermic reaction of a reaction system so as to increase a possibility for reaction runaway and to make the stable production of bulk syrup difficult.

Disclosure of Invention

20 The present invention has been made to solve the above-described problems occurring in the prior art, and it is an object of the present invention to provide a method for producing (meth)acrylate syrup, in which reaction runaway does not occur even in bulk polymerization, it is easy to control molecular weight and it is possible to form a high-molecular weight (meth)acrylate syrup.

25 To achieve the above object, the present invention provides a method for

PCT/KR2005/002973

RO/KR 08.11.2005

producing (meth)acrylate syrup by bulk polymerization, the method comprising initiating polymerization using the following components at a temperature of 50-80 °C:

- (a) 100 parts by weight of a (meth)acrylate ester monomer;
- (b) 0.005-5 parts by weight of a chain transfer agent;
- 5 (c) 0.0001-1.0 part by weight of a diacyl peroxide initiator; and
- (d) 0.5-3.0 moles, based on 1 mole of the component (c), of a tertiary amine cocatalyst.

The (meth)acrylate ester monomer used in the inventive method is not specifically limited and may be one generally used in the art. Examples of the
 10 (meth)acrylate ester monomer include a (meth)acrylate ester monomer with a C₁₋₁₂ alkyl group, and a polar (meth)acrylate ester monomer copolymerizable with said (meth)acrylate ester monomer. More specific examples of the (meth)acrylate ester monomer include methyl(meth)acrylate, ethyl(meth)acrylate, propyl(meth)acrylate, butyl(meth)acrylate, hexyl(meth)acrylate, isooctyl(meth)acrylate, 2-
 15 ethylhexyl(meth)acrylate, and isononyl(meth)acrylate.

Meanwhile, examples of the polar monomer copolymerizable with the (meth)acrylate ester monomer include carboxylic acid-containing monomers, such as (meth)acrylic acid, maleic acid, and fumaric acid, hydroxyl group-containing monomers, such as hydroxy(meth)acrylate, hydroxy(meth)methylacrylate,
 20 hydroxy(meth)ethylacrylate, hydroxy(meth)propylacrylate, and hydroxy(meth)butylacrylate, glycidyl group-containing monomers, such as glycidyl(meth)acrylate, and amine group-containing monomers, such as acrylamide.

These monomers may also be copolymerized with a third unsaturated monomer, such as styrene or benzoyl(meth)acrylate.

25 This polar monomer acts to impart cohesion to an adhesive and to improve

PCT/KR2005/002973

RO/KR 08.11.2005

adhesion.

Although the amount of use of the polar (meth)acrylate ester monomer copolymerizable with the (meth)acrylate ester monomer is specifically limited, it is generally 1-20 parts by weight based on 100 parts by weight of the (meth)acrylate ester monomer.

Examples of the diacyl peroxide initiator used in the inventive method include di-tert-butyl peroxide, dilauroyl peroxide, dibenzoyl peroxide, m-toluyyl benzoyl peroxide, di(3,5,5-trimethylhexanoyl) peroxide, didecanoyl peroxide, and distearyl peroxide. Particularly preferred is dilauroyl peroxide or dibenzoyl peroxide.

The diacyl peroxide initiators may be used alone or in a mixture of two or more thereof. The diacyl peroxide initiator is used in an amount of 0.0001-1.0 parts by weight, preferably 0.001-0.1 parts by weight, and more preferably 0.004-0.05 parts by weight, based on 100 parts by weight of the (meth)acrylate ester monomer. If the diacyl peroxide initiator is used in an amount of less than 0.0001 part by weight, the initiation efficiency of polymerization will be reduced and a phenomenon will occur where reaction continues to progress, and if it is used in amount of more than 1.0 part by weight, it will be difficult to control the temperature within a polymerization reactor.

Examples of the tertiary amine cocatalyst used in the inventive method include N,N'-dimethyl aniline, N, N'-dimethyl-p-toluidine, N,N'-dihydroxyethyl-p-toluidine, N,N'-dihydroxypropyl-p-toluidine, 4-dimethylamino)phenethyl alcohol, and 4-(dimethylamino)phenyl alcohol.

The tertiary amine cocatalysts may be used alone or in a mixture of two or mote thereof. The tertiary amine cocatalyst is used in an amount of 0.5-3 moles based on 1 mole of the diacyl peroxide initiator. If the tertiary amine cocatalyst is used in an amount of less than 0.5 moles, it will be difficult for the organic peroxide to initiate

PCT/KR2005/002973

RO/KR 08.11.2005

polymerization sufficiently, and if it is used in an amount of more than 3.0 moles, it will remain in a final product, resulting in deterioration in the product quality.

The chain transfer agent used in the inventive method is not specifically limited if it is an organic compound with a thiol group (-SH). Examples of the chain transfer agent include alkyl mercaptans, such as ethyl mercaptan, butyl mercaptan, hexyl mercaptan, and dodecyl mercaptan, thiophenols, such as phenyl mercaptan and benzyl mercaptan, carboxyl group-containing mercaptans, such as thioglycolic acid, 3-mercapto propionic acid, and thiosalicylic acid, hydroxyl group-containing mercaptans, such as 2-mercapto ethanol, and 3-mercapto-1,2-propanediol, and mercaptans with a combination of two or more of the above-described functional groups, such as pentaerythritol tetrakis(3-mercapto)propionate.

The chain transfer agent is used in an amount of 0.005-5 parts by weight based on 100 parts by weight of the (meth)acrylate ester monomer. If the amount of use of the chain transfer agent is less than 0.005 parts by weight, polymerization will rapidly progress and at the same time, uniform mixing within a reactor will not be made, and the molecular weight of the resulting polymer will excessively increase. If it is more than 5 parts by weight, polymerization rate will become slow and molecular weight will be excessively reduced, resulting in deterioration in the physical properties of a final product.

In the inventive method, a polymerization inhibitor may also be used. The polymerization inhibitor is not specifically limited if it is a compound capable of absorbing radicals to terminate radical reaction, for example, hydroquinone, or 4-methoxyphenol.

The reaction temperature in the inventive method is preferably as low as possible, insofar as it does not interfere with the smooth production of radicals by the

PCT/KR2005/002973

RO/KR 08.11.2005

diacyl peroxide and the tertiary amine cocatalyst. The reaction temperature meeting this condition is 50-80 °C, and preferably 60~75 °C. If the reaction temperature is less than 50 °C, reaction rate will become excessively low or the formation of radicals will become difficult, and if it is more than 80 °C, reaction rate will excessively increase, resulting in an excessive increase in the peak exothermic temperature, leading to a high possibility for reaction runaway.

After the initiation of reaction, the self-heat generation of the reaction system by the consumption of the initiator occurs, and the peak exothermic temperature of the reaction system reaches a range of 100-160 °C and preferably 120-140 °C. If the temperature of the reaction system exceeds 160 °C, a possibility for reaction runaway resulting from the production of radicals by heat will naturally increase, and if it is less than 100 °C, reaction will continue to progress with time even following the peak exothermic temperature, thus making it impossible to control the reaction. Although special warming and cooling are not required since the temperature of the reaction system following the peak exothermic temperature gradually naturally decreases, warming and cooling may also be carried out, if necessary.

Also, the time taken to reach the peak exothermic temperature is preferably shorter than 20 minutes. If the time taken to reach the peak exothermic temperature is longer than 20 minutes, it can be considered as the relatively slow progression of reaction. This slow progression of reaction makes the consumption rate of the initiator slow, so that heat generation continues to progress even following the peak exothermic temperature, polymerization rate constantly increases, and viscosity excessively increases, thus making the control of the reaction system difficult.

The (meth)acrylate syrup produced by the inventive method is in the form of a partially polymerized acrylate syrup with a conversion rate of 10-70%, and may be

PCT/KR2005/002973

RO/KR 08.11.2005

diluted with a new monomer, if necessary after the reaction.

The physical properties of the (meth)acrylate syrup synthesized by the inventive method are evaluated in the following manner.

1. Measurement of solid concentration

5 The concentration of solids in the syrup is measured by dropping about 0.1-1.3 g of the syrup onto a previously weighed aluminum dish, measuring the weight of the resulting dish, drying the syrup in an oven at 130 °C for 1 hour, and then, measuring the weight of the dried dish.

2. Measurement of viscosity

10 The viscosity of the syrup is measured with a Brookfield viscometer.

3. Measurement of molecular weight

The molecular weight of the syrup is measured in a multi-angle laser light scattering (GPC-Malls) detector (Waytt DAWN EOS) using tetrahydrofuran (THF) solvent at 0.8 mL/min.

15

Best Mode for Carrying Out the Invention

Hereinafter, preferred examples will be presented for a better understanding of the present invention. It is to be understood, however, that these examples are given
20 for illustrative purpose only and are not construed to limit the scope of the present invention.

Example 1

Into a 1-liter four-necked glass reactor equipped with a nitrogen gas inlet tube, a temperature sensor and a condenser, 570 g of 2-ethyl hexyl acrylate (2-EHA), 30 g of
25 acrylic acid (AA) and 0.24 g of dodecyl mercaptan (n-DDM), a chain transfer agent,

PCT/KR2005/002973

RO/KR 08.11.2005

were charged. The mixture was heated to a reaction temperature of 70 °C while removing dissolved oxygen with nitrogen stream for 30 minutes. Then, 0.025 g of 4-(dimethylamino)penethyl alcohol (DMAPA), as a tertiary amine cocatalyst, was added to the mixture and thoroughly mixed, to which 0.036 g of dibenzoyl peroxide (BPO), a diacyl peroxide initiator, was added to initiate reaction.

Temperature in the reaction was elevated to a peak exothermic temperature of 125 °C only within 8 minutes, and after 30 minutes, lowered to the reaction temperature set prior to the initiation of the reaction. After that, an increase in the viscosity of the reaction solution did not occur and the phenomena of heat generation and reaction runaway also did not appear.

After one hour, 285 g of 2-ethyl hexyl acrylate with room temperature and 15 g of acrylic acid were added for cooling, and 0.035 g of hydroquinone, a polymerization inhibitor, was added to terminate the reaction.

The concentration of solids in the partially polymerized syrup thus obtained was 49.9%, and the syrup had a viscosity of 10,800 centipoise (cP) and a molecular weight of 350,000.

Example 2

Into the reactor as described in Example, 570 g of butyl acrylate (BA), 30 g of acrylic acid (AA) and 0.24 g of dodecyl mercaptan (n-DDM) were charged. Reaction was carried out in the same manner as in Example 1 except that the reaction temperature was 60 °C, 0.06 g of a dilauroyl peroxide (LPO) initiator was used, and 285 of butyl acrylate with room temperature and 15 g of acrylic acid were added for cooling.

Temperature in the reaction was elevated to a peak exothermic temperature of 120 °C only within 6 minutes, and after 30 minutes, lowered to the reaction temperature set prior to the initiation of reaction. After that, an increase in the viscosity of the

PCT/KR2005/002973

RO/KR 08.11.2005

reaction solution did not occur and the phenomena of heat generation and reaction runaway also did not appear. The concentration of solids in the partially polymerized syrup thus obtained was 50.4%, and the syrup had a viscosity of 11,000 centipoise (cP) and a molecular weight of 350,000.

5 Example 3

Into the reactor as described in Example 1, the same monomers as in Example 1 were charged in the same amounts as in Example 1. Reaction was carried out in the same manner as in Example except that 0.58 g of pentaerythritol tetrakis(3-mercapto)propionate as a chain transfer agent, 0.036 g of dibenzoyl peroxide initiator
10 and 0.020 g of N,N'-dimethyl-p-toluidine (DMT) as a tertiary amine cocatalyst were used.

Temperature in the reaction was elevated to a peak exothermic temperature of 122 °C only within 8 minutes, and after 30 minutes, lowered to the reaction temperature set prior to the initiation of reaction. After that, an increase in the viscosity of the
15 reaction solution did not occur and the phenomena of heat generation and reaction runaway also did not appear. The concentration of solids in the partially polymerized syrup thus obtained was 47.8%, and the syrup had a viscosity of 7,700 centipoise (cP) and a molecular weight of 330,000.

Example 4

20 Reaction was carried out in the same manner as in Example 1 except that 600 g of 2-ethyl hexyl acrylate (2-EHA) was charged alone into the reactor as described in Example 1, without using acrylic acid (AA).

Temperature in the reaction was elevated to a peak exothermic temperature of 126 °C only within 8 minutes, and after 30 minutes, lowered to the reaction temperature
25 set prior to the initiation of reaction. After that, an increase in the viscosity of the

PCT/KR2005/002973

RO/KR 08.11.2005

reaction solution did not occur and the phenomena of heat generation and reaction runaway also did not appear. The concentration of solids in the partially polymerized syrup thus obtained was 47.2%, and the syrup had a viscosity of 8,000 centipoise (cP) and a molecular weight of 360,000.

5 Comparative Example 1

Reaction was carried out in the same manner as in Example 1 except that the tertiary amine cocatalyst was not used. Temperature in the reaction reached a very low peak exothermic temperature of 76 °C after 10 minutes. Then, the reaction continued to progress so that an increase in viscosity continuously occurred, thus making stirring
10 impossible. For this reason, the reaction was forcibly terminated.

Comparative Example 2

Reaction was performed in the same manner as in Example 1 except that 4-(dimethylamino)penethyl alcohol (DMPA) as a tertiary amine cocatalyst was used in an amount of 0.4 moles (0.010 g) based on 1 mole of dibenzoyl peroxide as an initiator.
15 Temperature in the reaction reached a low peak exothermic temperature of 95 °C after 20 minutes. Then, the reaction continued to progress so that an increase in viscosity continuously occurred, thus making stirring impossible. For this reason, the reaction was forcibly terminated.

Comparative Example 3

20 Reaction was carried out in the same manner as in Example 1 except that 4-(dimethylamino)penethyl alcohol (DMPA) as a tertiary amine cocatalyst was used in an amount of 3.5 moles (0.088 g) based on dibenzoyl peroxide as an initiator. The reaction progressed very slowly and showed yellowing by an excess of the amine.

Example 4

2.5 Reaction was carried out in the same manner as in Example 1 except that the

PCT/KR2005/002973

RO/KR 08.11.2005

reaction temperature was changed to 90 °C. Temperature in the reaction reached 170 °C within 4 minutes, and heat generation continued to progress without a reduction in the reaction temperature. Also, the reaction solution showed fog by the volatilization of the monomers and become impossible to stir. For this reason, the reaction was
5 forcibly terminated.

Comparative Example 5

Reaction was carried out in the same manner as in Example 1 except that the chain transfer agent was not used. Temperature in the reaction reached 170 °C within 8 minutes and then, within 30 minutes, lowered to the reaction temperature prior to the
10 initiation of reaction. However, the viscosity of the reaction solution was excessively increased to make stirring impossible. For this reason, the reaction was forcibly terminated.

Industrial Applicability

15

As described above, in the inventive method for producing (meth)acrylate syrup, a runaway reaction does not occur even in bulk polymerization, it is easy to control molecular weight and it is possible to form a high-molecular weight (meth)acrylate syrup without stirring failure.

20

The inventive method for producing (meth)acrylate syrup uses the exothermic heat of a reaction system after the initiation of polymerization, so that the peak exothermic temperature of the reaction system is reached within a short time together with the rapid degradation of the initiator and the termination of the reaction within a short time, and after that, the reaction no longer progresses. Thus, according to the
25 inventive method, it is possible to stably produce a partially polymerized (meth)acrylate

WO 2006/043751**PCT/KR2005/002973****PCT/KR2005/002973**
RO/KR 08.11.2005

syrup.

PCT/KR2005/002973

RO/KR 08.11.2005

What Is Claimed Is:

1. A method for producing (meth)acrylate syrup by bulk polymerization, the method comprising initiating polymerization using the following components at a
5 temperature of 50-80 °C:
- (a) 100 parts by weight of a (meth)acrylate ester monomer;
 - (b) 0.005-5 parts by weight of a chain transfer agent;
 - (c) 0.0001-1.0 part by weight of a diacyl peroxide initiator; and
 - (d) 0.5-3.0 moles, based on 1 mole of the component (c), of a tertiary amine
10 cocatalyst.
2. The method of Claim 1, wherein the diacyl peroxide initiator is at least one selected from the group consisting of di-tert-butyl peroxide, dilauroyl peroxide, dibenzoyl peroxide, m-toluyyl benzoyl peroxide, di(3,5,5-trimethylhexanoyl) peroxide,
15 didecanoyl peroxide, and distearyl peroxide.
3. The method of Claim 1, wherein the tertiary amine cocatalyst is at least one aromatic tertiary amine compound selected from the group consisting of N,N'-dimethyl aniline, N, N'-dimethyl-p-toluidine, N,N'-dihydroxyethyl-p-toluidine, N,N'-
20 dihydroxypropyl-p-toluidine, 4-dimethylamino)phenethyl alcohol, and 4-(dimethylamino)phenyl alcohol.
4. The method of Claim 1, wherein the reaction system reaches a peak exothermic temperature of 100-160 °C within the initiation of the polymerization.

25

PCT/KR2005/002973
RO/KR 08.11.2005

5. The method of Claim 1, wherein the syrup is a partially polymerized (meth)acrylate syrup with a conversion rate of 10-70%.

5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2005/002973

A. CLASSIFICATION OF SUBJECT MATTER**IPC7 C08F 2/02, C08F 290/04**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7 C08F 2/02, C08F 290/04

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean Patents and applications for inventions since 1975

Korean Utility models and applications for Utility models since 1975

Japanese Utility models and application for Utility models since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP 11-228645 A (MITSUBISHI RAYON CO., LTD) 24 August 1999 see the whole document	1-5
Y	JP 12-313704 A (SOKEN CHEM & ENG CO., LTD) 14 November 2000 see the whole document(especially, detailed description [002]), cited in application	1-5
A	KR 1995-9831 B1 (LG Chem. LTD) 29 August 1995 see the whole document	1-5
A	KR 1988-352 B1 (LORD CORPORATION) 20 March 1988 see the whole document	1-5



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 DECEMBER 2005 (14.12.2005)

Date of mailing of the international search report

16 DECEMBER 2005 (16.12.2005)

Name and mailing address of the ISA/KR



Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

BAHN, Yong Byung

Telephone No. 82-42-481-5539



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2005/002973

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 11-228645 A	24.08.1999	NONE	
JP 12-313704 A	14.11.2000	NONE	
KR 1995-9831 B1	29.08.1995	NONE	
KR 1988-352 B1	20.03.1988	DE3304816A1	18.08.1983
		EP86469A1	24.08.1983
		EP86469B1	30.01.1985
		GB2116185A1	21.09.1983
		GB2116185B2	04.12.1985
		JP58147477A2	02.09.1983
		JP62028993B4	23.06.1987
		US4452944A	05.06.1984

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.